# PICASSO

Rectified Glazed Floor Tile

TESSCERA™




**ACTUAL SIZE DETAIL**






Bianco



Ice



Grigio



Nero

V3 Shades

>6 Mohs

ColdRes

RET Rectified

| **SIZE & PACKING INFO** | Pcs./Ctn. | $m^2$/Ctn. | Ctn./Pallet | kg/Ctn. |
|---|---|---|---|---|
| 30 x 60cm | 8 | 1,44 | 40 | 28 |
| 60 x 60cm | 4 | 1,44 | 40 | 29 |


Coefficient of Friction test results exceed A.D.A recommendations ASTM C-1028 >0.60 wet DCOF >0.42


**PRODUCT DESCRIPTION**

Rectified 30 x 60 & 60 x 60cm Glazed Floor Tile
Available in Matt, Lapatto and R11 anti-slip finishes.
Six 60 x 60cm faces

**PICASSO**
**BIANCO & ICE**


TESSCERA™






**PICASSO**
**GRIGIO & NERO**

TESSCERA™





# PICASSO PRODUCT SPECIFICATION

GLAZED FLOOR TILE
Pressed Ceramic Tiles International Norm
ISO 13006-10545/98
GROUP: B1

| No. | Icon | Test item | Unit | Requirements of Standard | | Specification | Requirement |
|---|---|---|---|---|---|---|---|
| 1 |  | Dimensional variation | (%) | length of side | ±0.6 | < 0.6 | Qualified |
| 2 |  | Side straightness | (%) | ± 0.5 | | < 0.5 | Qualified |
| 3 |  | Squareness | (%) | ± 0.6 | | < 0.6 | Qualified |
| 4 |  | Surface flatness | (%) | Center curvature degree | ± 0.5 | < 0.5 | Qualified |
| | | | | Warping degree | ± 0.5 | < 0.5 | Qualified |
| | | | | Side curvature degree | ± 0.5 | < 0.5 | Qualified |
| 5 |  | Surface quality | —- | Sighting vertically at a distance of 0.8 meter away from the tile no defect on surface is observed in at least 95% of the tile | | conformed | Qualified |
| 6 |  | Breaking strength | N | When thickness ≥ 7.5mm the Average value ≥ 1100 | | > 1100 | Qualified |
| 7 |  | Rupture modulus | Mpa | Average value ≥ 30 individual ≥ 27 | | > 30 > 30 | Qualified |
| 8 |  | Abrasion resistance | Revs | 1500 | | > 1500 | Qualified |
| 9 |  | Hardness | MOHS | Mohs Scale | | > 6 | Qualified |
| 10 |  | Frost resistance | —- | No cracking after test | | conformed | Qualified |
| 11 |  | Resistance to acids & alkalis | —- | not less than grade GB | | Grade GA | Qualified |
| 12 |  | Chemical resistance | —- | not less than grade GB | | Grade GA | Qualified |
| 13 |  | Slip resistance | R | Ramp slip rating test | | R11 | Exterior |
| | | | DCoF | DCoF: 0.42 | | >0.42 | Matt/ Exterior |